

10E Aluminium Bronze Wire

Material Data Sheet

Introduction

This data sheet is offered as guidance for our standard range of products. Additional product variants and technical information, including MSDS sheets, are available from Metallisation

Related Specifications

BS EN ISO 24373:2009-S Cu 6100 (CuAl7)

Typical Composition

Typical composition of material given by % weight.

| Element | Minimum | Maximum |
|--------------|---------|---------|
| Al | 6 | 8.5 |
| Mn | | 0.5 |
| Pb | | 0.02 |
| Si | | 0.2 |
| Zn | | 0.2 |
| Others Total | | 0.4 |
| Cu | Balance | |

Packaging Form

| Packaging | Weight (Kg) | Tolerance (Kg) |
|--------------------------|-------------|----------------|
| Coil (Paper/VCI Wrapped) | 20KG | +/-0.5KG |
| MIG (D300) | 15KG | +/-0.1KG |

Metallisation Ltd., Peartree Lane, Dudley, West Midlands, DY2 0XH, UK
Tel: +44 (0)1384 252464 Fax: +44 (0)1384 237196
Visit our website at www.metallisation.com
Registered in England No. 270156. Registered office: Peartree Lane, Dudley, DY2 0XH
QSD 4/6/3

